

Listing of Claims:

Claim 1. (original) Use of glass compositions with antimicrobial and/or disinfectant effect in materials for tooth restoration, excepting implants, in the field of fillings, wherein the filling is a material selected from the following group:

- a composite material
- a glasionomer cement
- a compomer,

wherein the glass composition comprises the following components (in percentage by weight on an oxide basis)

SiO ₂	0 – 99.5 percent by weight
P ₂ O ₅	0 – 80 percent by weight
SO ₃	0 – 40 percent by weight
B ₂ O ₃	0 – 80 percent by weight
Al ₂ O ₃	0 – 30 percent by weight
Li ₂ O	0 – 30 percent by weight
Na ₂ O	0 – 40 percent by weight
K ₂ O	0 – 30 percent by weight
CaO	0 – 25 percent by weight
MgO	0 – 15 percent by weight
SrO	0 – 30 percent by weight
BaO	0 – 40 percent by weight
ZnO	0 – < 15 percent by weight
TiO ₂	0 – 10 percent by weight
ZrO ₂	0 – 15 percent by weight
CeO ₂	0 – 10 percent by weight
Ag ₂ O	0.01 – 5 percent by weight
F	0 – 70 percent by weight
J	0 – 10 percent by weight
Fe ₂ O ₃	0 – 5 percent by weight

and if necessary trace elements and/or normal refining agents in commodity quantities, wherein the sum of SiO₂ + P₂O₅ + SO₃ + B₂O₃ + Al₂O₃ is greater than 20 percent by weight and a

maximum of 99.5 percent by weight and the sum of

$\text{ZnO} + \text{Ag}_2\text{O} + \text{CuO} + \text{GeO}_2 + \text{TeO}_2 + \text{Cr}_2\text{O}_3 > 0.01$ percent by weight.

Claim 2. (original) Use of glass compositions with antimicrobial and/or disinfectant effect in materials for tooth restoration, excepting implants, wherein the glass composition comprises the following components (in percentage by weight on an oxide basis):

SiO_2	0 – 99.5 percent by weight, preferably 0 – 80 percent by weight
P_2O_5	0 – 80 percent by weight
SO_3	0 – 40 percent by weight
B_2O_3	0 – 80 percent by weight
Al_2O_3	0 – 30 percent by weight
Li_2O	0 – 30 percent by weight
Na_2O	0 – 40 percent by weight
K_2O	0 – 30 percent by weight
CaO	0 – 25 percent by weight
MgO	0 – 15 percent by weight
SrO	0 – 30 percent by weight
BaO	0 – 40 percent by weight
ZnO	0 – < 15 percent by weight, preferably 5 – < 15 percent by weight
F	0 – 65 percent by weight
J	0 – 10 percent by weight
Fe_2O_3	0 – 5 percent by weight
Ag_2O	0.01 – 5 percent by weight

and if necessary trace elements and/or normal refining agents in commodity quantities, wherein the sum of $\text{SiO}_2 + \text{P}_2\text{O}_5 + \text{SO}_3 + \text{B}_2\text{O}_3 + \text{Al}_2\text{O}_3$ is greater than 20 percent by weight and a maximum of 99.5 percent by weight, in particular a maximum of 80 percent by weight.

Claim 3. (currently amended) Application according to ~~any one of Claims 1 or 2~~claim 1 in coating, filling or veneering materials for ceramic dental superstructures.

Claim 4. (currently amended) Application according to ~~any one of Claims 1 through 3~~claim 1, characterized in that the glass composition comprises ZnO in the range of 0.25 to < 15

percent by weight, preferably 2.5 to 10 percent by weight.

Claim 5. (currently amended) Application according to ~~any one of Claims 1 through 4~~claim 1, characterized in that the glass composition comprises Ag_2O in the range of 0.05 to 2 percent by weight, in particular preferably 0.5 to 2 percent by weight.

Claim 6. (currently amended) Application according to ~~any one of Claims 1 through 5~~claim 1, characterized in that the sum $\text{BaO} + \text{SrO}$ is greater than 10 percent by weight.

Claim 7. (original) Ion-releasing glass composition with antimicrobial effect for application as materials for tooth restoration, in particular in materials for fillings, in combination with materials for fillings, in particular selected from glasionomers, composites, compomers, wherein the glass composition comprises the following components (in percent by weight on an oxide basis):

P_2O_5	> 66 – 80 percent by weight
SO_3	0 – 40 percent by weight
B_2O_3	0 – 1 percent by weight
Al_2O_3	> 6.2 – 10 percent by weight
SiO_2	0 – 10 percent by weight
Li_2O	0 – 25 percent by weight
Na_2O	9 – 20 percent by weight
CaO	0 – 25 percent by weight
MgO	0 – 15 percent by weight
SrO	0 – 15 percent by weight
BaO	0 – 15 percent by weight
ZnO	0 – < 15 percent by weight
Ag_2O	0 – 5 percent by weight
CuO	0 – 10 percent by weight
GeO_2	0 – 10 percent by weight
TeO_2	0 – 15 percent by weight
Cr_2O_3	0 – 10 percent by weight
J	0 – 10 percent by weight

F 0 – 3 percent by weight

wherein the sum of $\text{ZnO} + \text{Ag}_2\text{O} + \text{CuO} + \text{GeO}_2 + \text{TeO}_2 + \text{Cr}_2\text{O}_3 + \text{J} > 0.01$ percent by weight.

Claim 8. (original) Ion-releasing glass composition with antimicrobial effect for application as materials for tooth restoration, in particular in materials for fillings, in combination with materials for fillings, in particular selected from glasionomers, composites, compomers, wherein the glass composition comprises the following components (in percent by weight on an oxide basis):

P_2O_5	> 66 – 80 percent by weight
SO_3	0 – 40 percent by weight
B_2O_3	0 – 1 percent by weight
Al_2O_3	0 – 3.9 percent by weight
SiO_2	0 – 10 percent by weight
CaO	0 – 25 percent by weight
MgO	0 – 15 percent by weight
SrO	0 – 15 percent by weight
BaO	0 – 15 percent by weight
ZnO	0 – < 15 percent by weight
Ag_2O	0 – 5 percent by weight
CuO	0 – 10 percent by weight
GeO_2	0 – 10 percent by weight
TeO_2	0 – 15 percent by weight
Cr_2O_3	0 – 10 percent by weight
J	0 – 10 percent by weight
F	0 – 3 percent by weight

wherein the sum of $\text{ZnO} + \text{Ag}_2\text{O} + \text{CuO} + \text{GeO}_2 + \text{TeO}_2 + \text{Cr}_2\text{O}_3 + \text{J} > 1$ percent by weight.

Claim 9. (original) Ion-releasing glass composition with antimicrobial effect for application as materials for tooth restoration, in particular in materials for fillings, in combination with materials for fillings, in particular selected from glasionomers, composites, compomers, wherein the glass composition comprises the following components (in percent by weight on an oxide basis):

P_2O_5	> 45 – 90 percent by weight
B_2O_3	0 – 60 percent by weight
SiO_2	0 – 40 percent by weight
Al_2O_3	0 – 20 percent by weight
SO_3	0 – 30 percent by weight
Li_2O	0 – 0.1 percent by weight
Na_2O	0 – 0.1 percent by weight
K_2O	0 – 0.1 percent by weight
CaO	0 – 40 percent by weight
MgO	0 – 40 percent by weight
SrO	0 – 15 percent by weight
BaO	0 – 40 percent by weight
ZnO	0 – < 15 percent by weight
Ag_2O	0 – 5 percent by weight
CuO	0 – 15 percent by weight
Cr_2O_3	0 – 10 percent by weight
J	0 – 10 percent by weight
TeO_2	0 – 10 percent by weight
GeO_2	0 – 10 percent by weight
TiO_2	0 – 10 percent by weight
ZrO_2	0 – 10 percent by weight
La_2O_3	0 – 10 percent by weight
Nb_2O_3	0 – 5 percent by weight
CeO_2	0 – 5 percent by weight
Fe_2O_3	0 – 5 percent by weight
WO_3	0 – 5 percent by weight
Bi_2O_3	0 – 5 percent by weight
MoO_3	0 – 5 percent by weight

wherein the sum of $ZnO + Ag_2O + CuO + GeO_2 + TeO_2 + Cr_2O_3 + J > 0.001$ percent by weight.

Claim 10. (original) Ion-releasing glass composition with antimicrobial effect for application as materials for tooth restoration, in particular in materials for fillings, in combination with

materials for fillings, in particular selected from glasionomers, composites, compomers, wherein the glass composition comprises the following components (in percent by weight on an oxide basis):

SiO ₂	40 – 80 percent by weight
B ₂ O ₃	5 – 40 percent by weight
Al ₂ O ₃	0 – 10 percent by weight
P ₂ O ₅	0 – 30 percent by weight
Li ₂ O	0 – 25 percent by weight
Na ₂ O	0 – 25 percent by weight
K ₂ O	0 – 25 percent by weight
CaO	0 – 25 percent by weight
MgO	0 – 15 percent by weight
SrO	0 – 15 percent by weight
BaO	0 – 15 percent by weight
ZnO	0 – < 15 percent by weight
Ag ₂ O	0.01 – 5 percent by weight
CuO	0 – 10 percent by weight
GeO ₂	0 – 10 percent by weight
TeO ₂	0 – 15 percent by weight
Cr ₂ O ₃	0 – 10 percent by weight
J	0 – 10 percent by weight
F	0 – 10 percent by weight

wherein the sum of ZnO + Ag₂O + CuO + GeO₂ + TeO₂ + Cr₂O₃ + J ranges between 5 and 70 percent by weight.

Claim 11. (currently amended) Glass composition according to ~~any one of Claims 7 through 10~~ claim 7, characterized in that the glass composition comprises ZnO in the range of 0.25 to < 15 percent by weight, preferably 2.5 to 10 percent by weight.

Claim 12. (currently amended) Glass composition according to ~~any one of Claims 7 through 11~~ claim 7, characterized in that the glass composition comprises Ag₂O in the range of 0.05 to 2 percent by weight, preferably 0.5 to 2 percent by weight.

Claim 13. (currently amended) Glass composition according to ~~any one of Claims 7 through 12~~claim 7, characterized in that the glass composition contains BaO and SrO and the sum of BaO + SrO is greater than 10 percent by weight.

Claim 14. (currently amended) Ion-releasing glass composition according to ~~any one of Claims 7 through 13~~claim 7, characterized in that at least two vitreous phases are formed in the glass composition.

Claim 15. (original) Ion-releasing glass composition according to Claim 14, characterized in that in the glass composition at least two vitreous phases exhibit different compositions.

Claim 16. (currently amended) Ion-releasing glass composition according to ~~any one of Claims 14 or 15~~claim 14, characterized in that the glass composition is a borosilicate glass composition.

Claim 17. (original) Ion-releasing glass ceramic with antimicrobial effect for application as materials for tooth restoration, in particular in materials for fillings, in combination with materials for fillings, in particular selected from glasionomers, composites, compomers, wherein the base glass of the glass ceramic comprises the following components (in percent by weight on an oxide basis):

SiO₂ 20 – 90 percent by weight

CaO 0 – 45 percent by weight

Na₂O 0 – 40 percent by weight

P₂O₅ 0 – 15 percent by weight

Ag₂O 0.01 – 5 percent by weight

ZnO 0 – 20 percent by weight

wherein the sum of ZnO + Ag₂O + CuO + GeO₂ + TeO₂ + Cr₂O₃ + J is greater than 0.001 percent by weight.

Claim 18. (original) Ion-releasing glass ceramic according to Claim 17, characterized in that the crystalline main phases comprise alkali-alkaline earth -silicate and/or alkali-silicate and/or

alkaline earth-silicate, excepting a glass ceramic with the sole crystalline main phase $1 \text{ Na}_2\text{O} \cdot 2 \text{ CaO} \cdot 3 \text{ SiO}_2$ and the main phase $\text{Na}_4\text{Ca}_3\text{Si}_8\text{O}_{16}(\text{OH}_2)$.

Claim 19. (currently amended) Method for the production of an ion-releasing glass composition according to ~~any one of Claims 14 through 16~~claim 14, characterized in that the at least two phases are preserved by means of tempering in a temperature range $T_g \leq T \leq T_g + 300^\circ \text{C}$, wherein T_g is the transformation temperature of the glass.

Claim 20. (currently amended) Method for the production of an ion-releasing glass composition according to ~~any one of Claims 17 or 18~~claim 17, characterized in that the base glass for the glass ceramic is ground and subsequent to that a ceramizing of the powdery base glass takes place.

Claim 21. (currently amended) Method for the production of an ion-releasing glass composition according to ~~any one of Claims 17 or 18~~claim 17, characterized in that the base glass for the glass ceramic is ceramized first and is ground subsequent to that.

Claim 22. (currently amended) Glasionomer cement for dental applications comprising:
a polymer which contains free carboxylic acid groups,
an ion-releasing glasionomer glass composition as well as an ion-releasing antimicrobial glass composition or
an ion-releasing antimicrobial glass ceramic according to ~~any one of Claims 7 through 18~~claim 7.

Claim 23. (original) Glasionomer cement according to Claim 22 characterized in that 1 – 90 percent by weight of the total composition is an ion-releasing glass/glass ceramic composition, wherein the ion-releasing glass composition comprises an ion-releasing antimicrobial glass or an ion-releasing glass ceramic or is a mixture of ion-releasing glasionomer composition with an ion-releasing antimicrobial glass composition or an ion-releasing glass ceramic.

Claim 24. (currently amended) Glasionomer cement according to ~~any one of Claims 22 or 23~~claim 22, characterized in that the Ag_2O content > 0.01 percent by weight.

Claim 25. (currently amended) Glassionomer cement according to ~~any one of Claims 22 through 24~~claim 22, characterized in that the ratio of antimicrobial glass composition/glassionomer cement and/or fillings > 0.001 .

Claim 26. (currently amended) Glassionomer cement according to ~~any one of Claims 22 through 25~~claim 22, characterized in that the ratio of antimicrobial glass composition/glassionomer cement and/or fillings < 200 , preferably less than 100, quite preferably less than 10.

Claim 27. (currently amended) Coating or veneering material for ceramic dental superstructures, comprising
a base material, preferably a filling, in particular selected from:
a composite material,
a glassionomer cement,
a compomer,
an ion-releasing antimicrobial glass composition or an ion-releasing glass ceramic
according to ~~any one of Claims 7 through 18~~claim 7.

Respectfully submitted,



John F. Hoffman
Registration No. 26,280

Attorney for Applicant

JFH/pmp

BAKER & DANIELS
111 East Wayne Street, Suite 800
Fort Wayne, IN 46802

Date: October 10, 2006